

SIALON FLUORESCENT MATERIAL AND METHOD FOR PRODUCING THE SAME

Patent number: JP2004277663
Publication date: 2004-10-07
Inventor: HIROSAKI NAOTO; MITOMO MAMORU; MIYAZAKI SUSUMU; KAIHARA TAKAYOSHI
Applicant: NAT INST FOR MATERIALS SCIENCE; SUMITOMO CHEMICAL CO
Classification:
- international: C09K11/08; C09K11/64; C09K11/80; C09K11/08; C09K11/64; C09K11/77; (IPC1-7): C09K11/08; C09K11/64; C09K11/80
- european:
Application number: JP20030074580 20030318
Priority number(s): JP20030074580 20030318

Report a data error here

Abstract of JP2004277663

PROBLEM TO BE SOLVED: To provide a fluorescent material without having brightness reduction by solving a problem such that conventional fluorescent material is excited by the irradiation of an exciting source such as light or an electric beam having a high energy and emits light, and as a result, the brightness of the fluorescent material decreases.

SOLUTION: The subject method for producing a sialon fluorescent material exhibiting a high brightness is provided by preparing a metal compound mixture capable of constituting the sialon fluorescent material containing a metal element M (M is ≥ 1 kind selected from the group consisting of Li, Ca, Mg, Y and lanthanide metals) by burning, and burning the mixture by keeping $\geq 2,000$ [deg.]C and $\leq 2,400$ [deg.]C temperature range under nitrogen atmosphere of ≥ 0.2 MPa and ≤ 100 MPa.

COPYRIGHT: (C)2005,JPO&NCIP

Data supplied from the esp@cenet database - Worldwide